

Acetal Copolymer
KEPITAL®

FM2020

Grade.

			KEPITAL FM2020
	ASTM D792	–	1.43
23 , 60%RH	ASTM D570	%	0.22
190 , 2.16 kg	ASTM D1238	g/10min	10
10 /min	ASTM D3418		165
4.6kg _f /cm ²	ASTM D648		124
18.6kg _f /cm ²	ASTM D696	10 ⁻⁵ cm/cm/	13
20 80	UL94	–	HB
23	ASTM D638	kg _f /cm ²	635
23	ASTM D638	%	50
23	ASTM D790	kg _f /cm ²	920
23	ASTM D790	kg _f /cm ²	27,000
t 2mm	ASTM D732	kg _f /cm ²	
Izod t 3.2mm	ASTM D256	kg _f · cm/cm	6.8
Rockwell M scale	ASTM D785	–	M80
10 ⁶ Hz	ASTM D150	–	
10 ⁶ Hz	ASTM D150	–	
	ASTM D257	· cm	1 10 ¹⁶
	ASTM D257		1 10 ¹⁴
	ASTM D149	kV/mm	
(//) t 3mm, 100mm		%	2.0

) 1.
2.